S T A T E **O F** **T E N N E S S E E**

(Rev. 5-18-15) January 1, 2015

Supplemental Specifications - Section 200

of the

Standard Specifications for Road and Bridge Construction

January 1, 2015

Subsection 204.06 – 2 (pg.152-154), 5-18-15**;** Replace Tables 204.06 with the following:
1. General Use Flowable Fill

Table 204.06-2: Specification Limits for General Use Flowable Fill

Property	Specification Limit
Load Application (ASTM D6024)	24 hours maximum in any condition
Consistency	15 inches minimum tested as specified in this **204.06.B.1**

Page 153

2. Excavatable Flowable Fill (EFF)

Table 204.06-3: Specification Limits for EFF

Property	Specification Limit
Air content (ASTM D6023)	Maximum 30% [(1)]
Load Application (ASTM D6024)	24 hours maximum in any condition
Consistency	15 inches minimum as tested per **204.06.B.1**
Compressive strength (ASTM D4832) [(2)]	30 psi minimum at 28 days

[(1)] When using air entrained mixture design

[(2)] ASTM D4832 4 x 8 inch cylinder molds may be used. The preferred capping method to be used is wetsuit neoprene restrained in rigid retainers.

3. Early Strength Flowable Fill (ESFF)

Table 204.06-4: Specification Limits for ESFF

Property	Specification Limit
Air content (ASTM D6023)	Maximum 30% (1)
Load Application (ASTM D6024)	6 hours maximum in any condition
Consistency	15 inches minimum as tested per **204.06.B.1**
Compressive strength (ASTM D4832) (2)	30 psi minimum at 24 hours

(1) When using air entrained mixture design

(2) ASTM D4832 4 x 8 inch cylinder molds may be used. The preferred capping method to be used is wetsuit neoprene restrained in rigid retainers.